

AFCONA - 3750



Chemical Composition

Polymeric fluorocarbon compound

Product general description

Wetting, levelling and flow control agent for solvent-based coatings with excellent anti-crater properties.

Product Properties:

AFCONA – 3750 is 52% solid version of AFCONA – 3700 for better handling in winter because the viscosity of AFCONA – 3700 very high, almost not pourable in winter. AFCONA – 3750 is a highly fluorocarbon modified acrylic polymer. It has very low surface tension and therefore, it can substitute and perform as silicones without the side effects of silicones.

AFCONA - 3750 reduces drastically surface tension of organic coating systems. This, together with good compatibility in most solvent-based systems and with minimal foam stabilizing effect, makes it very effective as an anti-crater and flow control agent for all solvent based coating.

Due to the low surface tension, it gives very good substrate wetting and normally recommended to combine with a silicone based leveling agent to gives optimum performance on leveling, anti-crater as well as flow control.

AFCONA – 3750 is widely used, especially in refinish topcoats as a good prevention for crater formation, caused by different environment of application sites.

AFCONA-3750 is an excellent anti-crater and substrate wetting agent. AFCONA-3750 is especially suitable for:

- 1) stoving enamels based on alkyd, acrylic and polyester resins
- 2) polyurethane coatings
- 3) two-pack epoxy compounds
- 4) air-drying alkyd systems
- 5) UV coating

Product Specification

Non-volatile matter	50 - 53% (150°C,0.5h)
Density	1,04 - 1,06g/cm ³ (20°C)
Solvent	PMA
The refractive index	1,420 - 1,430 (25°C)
Flash point	44°C
Gardner color	Max.3
Appearance	transparent to slight yellowish liquid (25°C)

Addition and dosage

0.1 – 1.0% on total formulation. In general, under normal conditions, the dosage is 0.1 – 0.5% based on total formulation

Incorporation

AFCONA-3750 should be added at the end of the batch preparation

Storage

AFCONA-3750 should be stored in a cool dry place. When kept in an original unopened container, it will keep up to 5 years from the date of manufacture. The expiry date is indicated on the container.

Packaging

30 kg and 210kg non-returnable containers

AFCONA ADDITIVES
Web Site : www.afcona.com

This information and all further technical advice are based on our present knowledge and experience. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used. We reserve the right to make any changes according to science and technological progress or further developments.

This version replaces all previous ones.