

AFCONA - 2021



Chemical Composition

Defoaming substances, silicone free

Product general description

A well balance silicone free defoamer on compatibility and defoaming performance.

Product properties

AFCONA-2021 is a silicone-free defoamer for various coating systems. It functions well during the application of paints and lacquers. Also prevents the entrapment of air during processing steps such as stirring, pumping etc.

AFCONA-2021 has very good compatibility with most resin systems. However, for in-can clarity and dry film transparency, the non-silicone defoamer AFCONA-2018 will be a better choice.

AFCONA-2021 is mainly used in wood coating system due to it good defoaming and acceptable in-can haziness.

AFCONA-2021 is especially suited for solvent based coatings if foam formation is a problem when applied by spraying or brushing.

AFCONA-2021 can be used in:

- 1) polyurethane coatings, non- acrylic based for wood.
- 2) acid-curing coatings for wood.
- 3) air-drying alkyd paints for decorative and protective coatings.
- 4) stoving systems for industrial application.
- 5) NC lacquers for wood, and general industrial and car refinish. .

Remark: AFCONA – 2021 is not suited for Acrylic based systems.

Product Specification

Solvent	Xylene
Density	0.85 – 0.87 g /cm ³ (20°C)
The refractive index	1.490 - 1.500 (25°C)
Flash point	32°C
Appearance	Clear to slightly yellow liquid (25°C)

Addition and dosage

0.1- 1.0% on total formulation. In general under normal conditions, the dosage is 0.30 – 0.50% based on total formulation.

Incorporation

AFCONA-2021 can be incorporated prior to processing. If added subsequently, good dispersion must be ensured.

Storage

AFCONA-2021 should be stored in a cool and dry place. When kept in an original unopened container, it will keep up for 5 years from the date of manufacture. The expiry date is indicated on the container.

Packaing

20kg and 170kg non-returnable containers

AFCONA ADDITIVES

Web Site : www.afcona.com

This information and all further technical advice are based on our present knowledge and experience. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used. We reserve the right to make any changes according to science and technological progress or further developments.

This version replaces all previous ones.