

# AFCONA - 4060



## Chemical Composition

Modified polyurethane polymer.

## Product general description

High molecular weight polymeric dispersant for deflocculation of all pigments .

## Product Properties:

AFCONA-4060 is a polymeric dispersant for stabilizing inorganic and organic pigments as well as carbon blacks. It has fairly stability performance, through effective steric hindrance, on all type of pigments.

This results in:

- Lower mill base viscosity
- higher colour strength
- Reduced flooding and floating

AFCONA – 4060 has below special properties and recommended in below systems :

- 1) AFCONA-4060 is a lower polar polymer compared to other AFCONA 4000 series. The price for this product is relatively low thus the pigment stability performance is less comparing to AFCONA – 4050, AFCONA 4046 and AFCONA 4047.
- 2) AFCONA-4060 is recommended for baking paints especially coil coatings. It also can be used for other resin systems as long as it is compatible.

Note: AFCONA – 4060 will become slightly hazy at temperatures below 5° C. Heating up to uniformity. It will not influence the performance and quality of final product .

## Product Specification

Active ingredients	29 - 31%
Solvent	Butylacetate / Methoxy Propyl Acetate/ Xylene/ Sec-butanol
Density	0,93 – 0,95 g/cm <sup>3</sup>
Amine Value	6 - 16 mg KOH/g
Flash point	35°C
Colour	Max.6
Appearance	Clear to slightly hazy, yellow liquid

## Addition and dosage

Percent by weight Form of supply compare with pigments:

- 2.0 - 3.0% based on TiO<sub>2</sub> or extenders
- 2.0 - 4.0% based on inorganic pigments
- 20.0 - 40.0% based on organic pigments
- 20.0 - 60.0% based on carbon blacks.

## Incorporation

AFCONA-4060 should be added prior to the dispersion process.

## Storage

AFCONA-4060 should be stored in a cool dry place. When kept in an original unopened container, it will keep up to 5 years from the date of manufacture. The expiry date is indicated on the container.

## Packaging

25kg and 190 kg non-returnable containers

AFCONA Polymers Co., Ltd.  
Web Site : [www.afcona.com](http://www.afcona.com)

This information and all further technical advice are based on our present knowledge and experience. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used. We reserve the right to make any changes according to science and technological progress or further developments.