

AFCONA - 4474



Chemical Composition

Acrylate based Polymeric Dispersant .

Product general description

Acid based polymeric dispersant for coil and can coatings or any other acid curing system .

Product Properties:

AFCONA – 4474 is a very strong dispersant especially for TiO₂ dispersion in oil free polyester/melamine systems. This combination is commonly used in coil and can coating as well as in industrial baking paints.

AFCONA - 4474 is particularly suitable for the following applications:

- 1) -In coil and can coating applications the use of AFCONA – 4474 in TiO₂ dispersions will increase the **whiteness** as well as the **hiding power** of the coating. It will also reduce the viscosity of the system. Therefore higher pigment loading could be achieved
- 2) -Due to the pigment affinity group it is also a good dispersant for transparent iron oxide and other inorganic pigments
- 3) -It also can be used as an effective dispersant for other acid curing systems where dispersants contain amine values always affect the flocculation stability and curing time
- 4) -Baking paints based on polyester systems
- 5) -AFCONA 4474 is also very suitable for UPE & Epoxy systems due to the acid functional pigment affinity group. Common dispersant mostly contain amine values which always affect the self- and pot-life

Product Specification

Active ingredients	50 -54%
Solvent	n-butyl acetate/ Methoxyl Propyl Acetate
Density at 20°C	1,005 – 1,035 g/cm ³
Amine value	7 – 14 mg KOH/g
Flash point	45°C
Color	Max.18
Appearance	Clear to slightly haze, brownish liquid

Addition and dosage

Calculation method for the required amount of active ingredient on pigment:

TiO ₂	: 2 - 3%
Other inorganic pigments	: 2 - 4%
Organic pigments	: 20 - 40%
Carbon blacks	: 20 - 60%

Incorporation

AFCONA-4474 should be incorporated in the mill base before adding the pigments.

Storage

AFCONA-4474 should be stored in a cool dry place. When kept in an original unopened container, it will keep up to 5 years from the date of manufacture. The expiry date is indicated on the container.

Packaging

25kg and 190 kg non-returnable containers

AFCONA Polymers Co., Ltd.

Web Site : www.afcona.com

This information and all further technical advice are based on our present knowledge and experience. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used. We reserve the right to make any changes according to science and technological progress or further developments.

This version replaces all previous ones.