AFCONA - 4595



Chemical Composition

Special designed block copolymer.

Product general description

High molecular weight polymeric dispersant for de-flocculation of pigments in water-based decorative as well as industrial paints.

Product Properties:

AFCONA-4595 is a wetting and dispersing additive for water-based coatings and pigment concertrates. It prevents negative flocculation effects like; flooding and floating and improve the storage stability.

AFCONA-4595 is recommended for all kind of pigments. Also very suitable for transparent iron oxides.

It stabilize the pigments through effective steric hindrance and electric repulsion.

This all result in the concentrates in:

- lower viscosities and
- very stable dispersions with good storage stabilities
- high color strengths
- compatible with most architecture coating systems.

In the final coating in:

- no flooding and floating
- high color strength
- high gloss
- good storage stability
- low influence of water resistence

AFCONA-4595 is complete water-soluble and does not necessary has to be neutralize.

AFCONA-4595 is for optimum dispersing use no resin in grinding phase and general water-based colorant masterbatch, and also suitable for all kinds of water based acrchitecture and industrial coatings. For economic considerations, AFCONA-4595 can be combined with AFCONA-6225 to reduce the cost and also can keep the performance.

Product Specification

Non-volatile matter 39 -43% (120°C,0.5h)

Solvent Water

Density $1.02 - 1.06 \text{ g/cm}^3 (20^{\circ}\text{C})$

Tiphe refractive index 1.390 - 1.410 (25°C)

Acid value 7 - 15 mg KOH/g

Flash point >100°C

Appearance Transparent, brownish

liquid (25°C)

Addition and dosage

Active ingredient on pigment:

TiO2: 2 - 3%Other inorganic pigments: 2 - 5%Organic pigments: 20 - 40%Carbon blacks: 20 - 60%Transparent Iron Oxides: 5 - 15%

Incorporation

AFCONA-4595 should be incorporated in the mill base before adding the pigments.

Storage

AFCONA-4595 should be stored in a cool dry place. When kept in an original unopened container, it will keep up to 3 years from the date of manufacture. The expiry date is indicated on the container.

Packaging

30kg and 210 kg non-returnable plastic containers

AFCONA ADDITIVES

Web Site: www.afcona.com

This information and all further technical advice are based on our present knowledge and experience. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. Reference that enames used by other companies is neither a recommendation, nor does it imply that similar products could not be used. We reserve the right to make any changes according to science and technological progress or further developments.