

AFCONA - 5585



Chemical Composition

High molecular weight polyurethane block copolymer with pigment affinity groups.

Product general description

Solvent-free wetting and dispersing agent which based on water born polyurethane resin, applied in industrial coatings as well as architectural coatings.

Product Properties:

AFCONA – 5585 is an all-new designed water based polyurethane dispersant. It is suit for preparation of solvent and water based pigment concentrate. It also can be used in water based industrial coating as main dispersant.

The properties and applications of AFCONA-5585 as below:

- 1) AFCONA-5585 can stabilize carbon blacks and all organic pigments when used as main dispersant, It also can be used to disperse TiO₂ and other inorganic pigments.
- 2) AFCONA-5585 is not only soluble in water but also in organic solvent. So the concentrate can be prepared in solvent systems, such as long oil alkyd and etc. And It can be applied in architectural decorations.
- 3) AFCONA-5585 is VOC-free, and environment friendly.
- 4) AFCONA-5585 can be used to grind white-master batch, and it also can help the preparation of other colorant on sell, and to reduce or even solve the problems of color separation.

Note: AFCONA – 5585 will become hazy at temperature 5C or below. Heat up to 50°C and mix well before use. This will not influence the quality.

Product Specification

Active ingredients	≥96%
Density	0.99 – 1.13 g/cm ³
Amine Value	17 - 25 mgKOH/g
Flash point	>100°C
Appearance	Brownish liquid

Addition and dosage

Calculation method for the required amount of active ingredient on pigment:

Universal colorant:	
Inorganic pigment	:5 - 10%
Organic pigment	:10 - 20%
Primer/Under coat	:0.5-1.5% on total formula

Incorporation

AFCONA - 5585 should be added prior to the pigment grinding process.

Storage

AFCONA-5585 should be stored in a cool dry place. When kept in an original unopened container, it will keep up to 3 years from the date of manufacture. The expiry date is indicated on the container.

Packaging

25kg and 190 kg non-returnable containers

AFCONA Polymers Co., Ltd.
Web Site : www.afcona.com

This information and all further technical advice are based on our present knowledge and experience. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used. We reserve the right to make any changes according to science and technological progress or further developments.

This version replaces all previous ones.