

AFCONA - 6226



Chemical Composition

Fatty acid modified polyester.

Product general description

Dispersant and emulsifier for universal colourants and perform as colour acceptance additive.

Product Properties:

AFCONA-6226 is an improved version of AFCONA – 6225 where it based on more easy available raw materials. It gives better dispersing performance as well as better colour acceptance in decorative paints.

AFCONA – 6226 has below special properties comparing to AFCONA - 6225:

- 1)AFCONA-6226 is more hydrophilic where it can dissolve in water much easy than AFCONA – 6225. Thus pigment paste that based on AFCONA - 6226 will gives better colour strength.
- 2) AFCONA-6226 gives better pigment stability, colour development and lower colour paste viscosity.
- 3) AFCONA – 6226 also gives better colour acceptance in water based and alkyd based paint.

Note: AFCONA – 6226 will become slightly hazy at temperatures below 5° C. This will not influence the quality.

Product Specification

Non-volatile matter	≥ 96% (120°C,0.5h)
Density	0.95 – 1.05 g/cm ³ (20°C)
Amine Value	18 – 28 mg KOH/g
Acid Value	25 - 35 mg KOH/g
Appearance	Dark brown liquid(25°C)

Addition and dosage

Calculation method for the required amount of active ingredient on pigment:

Universal colourants:

5 - 10%	for inorganic pigments
10 - 20%	for organic pigments

Base-paints 0.5 - 1.5% on total based
Paints

Bentonites 15 - 25% on active
/thickeners substance

Incorporation

AFCONA – 6226 can be incorporated in the millbase or used as post additive for colour acceptance..

Storage

AFCONA-6226 should be stored in a cool dry place. When kept in an original unopened container, it will keep up to 5 years from the date of manufacture. The expiry date is indicated on the container.

Packaging

30kg and 200 kg non-returnable containers

AFCONA ADDITIVES

Web Site : www.afcona.com

This information and all further technical advice are based on our present knowledge and experience. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used. We reserve the right to make any changes according to science and technological progress or further developments.

This version replaces all previous ones.