

# AFCONA - 6530



## Chemical Composition

Modified Polyurethane and polyurea compound.

## Product general description

No VOC problem of AFCONA 6530, adjust viscosity in can. And improve anti-flooding and settlement prevention.

## Product Properties:

The rheology property of AFCONA-6530 depends on the interaction of dispersed particles in aqueous systems, the rheology property of polyurea would be enhanced through hydrogen bond. This will bring paint a kind of obvious non-Newtonian pseudoplastic fluid to improve the settlement prevention and anti-flooding in thick film coating. It is a solvent-free product, Thus no VOC problems, no adverse effects to gloss of coating film.

AFCONA 6530 is suitable for kinds of water-based coatings and water-based inks. It is recommended to be incorporated before grinding to increase the viscosity of concentrate, and then improve the efficiency of grinding.

The properties and advantages of AFCONA 6530 as below:

- 1) Adjust in-can viscosity, improve anti-flooding and settlement.
- 2) Low influence to leveling, or even will improve the leveling while provides anti-settlement and thickening.
- 3) Recommended to be used in aqueous and solventless systems.

Note: AFCONA – 6530 will become slightly hazy and non-uniform when kept at low temperature. This is the characteristic of AFCONA 6530. And make sure it has been mixed well before process.

## Product Specification

Non-volatile matter	≥98% (150°C,0.5h)
Density	1.02 – 1.06 g/cm <sup>3</sup> (20°C)
Gardner color	Max.5
Flash point	>100°C
Appearance	Clear to slightly hazy, yellow liquid(25°C)

## Addition and dosage

0.2-2.0% on total formulation. It is better to do experiments to make sure of the final addition.

## Incorporation

AFCONA – 6530 can be incorporated in stage of process. Good dispersion is required when incorporated at painting.

## Storage

AFCONA-6530 should be stored in a cool dry place. When kept in an original unopened container, it will keep up to 3 years from the date of manufacture. The expiry date is indicated on the container.

## Packaging

30kg and 200kg non-returnable plastic containers

AFCONA ADDITIVES

Web Site : [www.afcona.com](http://www.afcona.com)

This information and all further technical advice are based on our present knowledge and experience. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used. We reserve the right to make any changes according to science and technological progress or further developments.

This version replaces all previous ones.