

AFCONA - 7206



Chemical Composition

High molecular weight polymer, silicone free.

Product general description

AFCONA-7206 is an efficient defoamer and widely used in unsaturated polyester, polyacrylate, polyurethane and epoxy systems.

Product Properties:

AFCONA-7206 can destroy the foams efficiently whenever on the surface or in the solution, and also can improve the compactness of product's surface film, and improve the weather resistant and chemical resistant, as well as the aesthetics. Widely used in unsaturated polyester, polyacrylate, polyurethane and epoxy systems.

AFCONA - 7206 is solvent-free, and recommended to free radical polymerization systems of unsaturated polyester, vinyl, acrylate. and also can be used in epoxy and polyurethane resins.

The defoaming performance won't be affected by the temperature whatever lower or higher. Because of solvent-free, AFCONA - 7206 can be used in applications where low VOC are required.

Product Specification

Active ingredients	≥98%
Density	0.916 – 0.956 g/cm ³
Refractive index	1.513 - 1.533
Flash point	>100°C
Gardner Color	≤ 3
Appearance	Clear to slight yellowish viscous liquid

Addition and dosage

0.2- 1.0% on total formulation.

Incorporation

AFCONA 7206 can be added at any stage of process, and good dispersion is required.

Storage

AFCONA-7206 should be stored in a cool dry place. When kept in an original unopened container, it will keep up to 5 years from the date of manufacture. The expiry date is indicated on the container.

Packaging

25kg and 180 kg non-returnable containers

AFCONA Polymers Co., Ltd.

Web Site : www.afcona.com

This information and all further technical advice are based on our present knowledge and experience. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used. We reserve the right to make any changes according to science and technological progress or further developments.

This version replaces all previous ones.