

AFCONA - 2022



Chemical Composition

Polysiloxane based defoaming polymer.

Product general description

A strong defoamer with easy incorporation. AFCONA-2022 is the polysiloxane based version of AFCONA-2020.

Product properties

AFCONA-2022 prevents the formation of foam and blisters during the manufacturing and application of solvent-based and solvent-free coatings.

AFCONA-2022 is ideal for both, production and application processes, particularly curtain coating. If foaming occurs during packaging, AFCONA-2022 can be added slowly with increased stirring speed to accelerate bubble breakdown.

Due to the presence of polysiloxane, AFCONA-2022 has better de-aerating properties than AFCONA-2020, while AFCONA-2020 offers stronger anti-foam performance.

AFCONA-2022 offers better in-can transparency than AFCONA-2020.

AFCONA-2022 is recommended for:

- 1) Two-component systems based on polyurethane and epoxy resins.
- 2) Baking paints based on alkyd, acrylic, and saturated polyester resins.
- 3) Air-drying industrial coatings based on long- and medium-oil alkyd resins.
- 4) Protective coatings.

Product Specification

Solvent	Xylene/Butyl Acetate/ Propylene glycol methyl ether acetate/ Ethyl Acetate
Density	0.88 - 0.90 g/cm ³ (20°C)
Refractive index	1.458 - 1.468(25°C)
Flash point	30°C
Appearance	Clear, colorless to slightly yellow liquid(25°C)

Addition and dosage

0.1- 1.0% on total formulation. Under normal conditions, the dosage is 0.20 - 0.50% based on total formulation.

Incorporation

AFCONA-2022 can be incorporated prior to processing. If added subsequently, good dispersion must be ensured.

Storage

AFCONA-2022 shall be stored in cool and dry place away from direct sunlight. Shelf-life is 5 years from the date of manufacturer, if kept in original and unopened container. The expiring date is indicated on the package.

Packaging

25kg and 170kg non-returnable containers

For product safety information: please take reference of SDS.

AFCONA ADDITIVES

Web Site : www.afcona.com

This information and all further technical advice are based on our present knowledge and experience. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used. We reserve the right to make any changes according to science and technological progress or further developments.

This version replaces all previous ones.