

AFCONA - 4403



Chemical Composition

Modified polyacrylate polymer.

Product general description

High molecular weight polymeric dispersant for deflocculation of all type of pigments.

Product Properties:

AFCONA-4403 is an effective polymeric dispersant for stabilizing inorganic and organic pigments. It has very good stability performance, through effective steric hindrance, on all type of pigments.

This results in:

- improved gloss and DOI
- reduced flooding problems
- high colour strength

AFCONA-4403 is a better compatibility version of AFCONA – 4401. With the special modification it gives lower surface tension on the polymer. This character will allow the dispersant easier to penetrate to the surface of the pigment, thus this gives better wetting and faster grinding.

It has very wide compatibility from low polar to high polar systems, including nitrocellulose and Thermoplastic Acrylic. However care must be taken when used in combination with chlorinated polymers and/or epoxies systems, because in these systems it has a tendency to yellowing or gelling.

AFCONA-4403 can be used in all kinds of high quality solvent-based industrial coatings including automotive topcoats. The best performance is given in the following resin systems:

- Oil free Polyesters
- Thermosetting Acrylics
- Thermoplastic acrylics

Note: Due to the linear and symmetry structure, the viscosity reduction property of AFCONA-4403 is much less than the AFCONA polyurethane type of dispersants.

Product Specification

Active ingredients 54 -56%

Solvent	n-butyl acetate/ Sec-butanol/xylene /Methoxyl Propyl Acetate
Density at 20°C	0,93 – 0,97 g/cm ³
Amine value	34 – 44 mg KOH/g
Flash point	43°C
Color	Max.5

Addition and dosage

Calculation method for the required amount of active ingredient on pigment:

TiO2	: 2 - 3%
Other inorganic pigments	: 2 - 4%
Organic pigments	: 20 - 40%
Carbon blacks	: 20 - 60%

Incorporation

AFCONA-4403 should be incorporated in the mill base before adding the pigments.

Storage

AFCONA-4403 should be stored in a cool dry place. When kept in an original unopened container, it will keep up to 5 years from the date of manufacture. The expiry date is indicated on the container.

Packaging

25kg and 190 kg non-returnable containers

AFCONA ADDITIVES

Web Site : www.afcona.com/www.afcona.com.my

This information and all further technical advice are based on our present knowledge and experience. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used. We reserve the right to make any changes according to science and technological progress or further developments.

This version replaces all previous ones.